

## TEROSON WT S3000 AQUA

July 2022

## PRODUCT DESCRIPTION

TEROSON WT S3000 AQUA provides the following characteristics:

<b>Technology</b>	Abrasion-resistant chipping protection, multivarious dyable
<b>Base</b>	Aqueous synthetic resin dispersion
<b>Appearance</b>	black, grey, light

TEROSON WT S3000 AQUA is a coating compound based on an aqueous synthetic resin dispersion which can be spray-applied with UBC-guns, filler or paint pistols. Drying times are dependent on the thickness of the coating applied, on ambient temperatures and on the relative humidity of the ambient air. Drying is considerably faster if good ventilation and relatively high temperatures are provided. The dry film adheres well to zinc-coated and electro-coated steel sheet metal and to painted surfaces. Because of its high abrasion resistance and its good flexibility TEROSON WT S3000 AQUA offers excellent protection to scratches, stonchips and other such marks. TEROSON WT S3000 AQUA is processable / overpaintable with waterborne paints. When fully air dried (at the earliest after 6 hours) the coating can be painted over with standard vehicle refinish paint systems (including solvent born paints). After complete drying the coating can be sanded. TEROSON WT S3000 AQUA is temporarily resistant against fuels and cold cleaners. TEROSON WT S3000 AQUA is suitable for restoring the original structure after a repair.

**IMPORTANT: The following information is only valid for the light version!**

TEROSON WT S3000 AQUA also allows inking and mixing with water born refinish paints and is dilutable with deionised water. In case of dyeing TEROSON WT S3000 AQUA it is recommended not to exceed the addition of 30 vol.% of ready for use water born paint. By varying the mixing ratios, the spraying pressure and distance different surface textures can be obtained, from smooth to rough.

**Application areas:**

TEROSON WT S3000 AQUA is used for repair/touch up jobs of the underbody, wheel houses, front and rear areas (aprongs). It can be applied to visible parts of e.g. door sills as an overpaintable protection against road stone chip or as a protection against corrosion caused by salt and humidity. TEROSON WT S3000 AQUA is ideally suited to recreate the different surface textures produced at original manufacture, for the perfect visible repair. Its outstanding benefit are the multivarious possibilities of the dyeing the material. Scratches or other small injuries of the paint remains nearly invisible.

## TECHNICAL DATA

(Typical Test Results)

Colour:	white grey, black
Odour	slight odour of ammonia
Density:	approx. 1.2 to 1.25 g/cm <sup>3</sup>
Consistency:	liquid
Solids:	approx. 67 %
Sag resistance:	up to 1 mm wet

## ACOUSTIC DATA

(ONLY relevant for the black version)

Loss factor	approx. 0.1
DIN EN ISO 6721-3	
Temperature	20 °C
Frequency	200 Hz
Material	steel sheet 1 mm
Thickness ratio coating/ steel sheet	2 : 1

## PRELIMINARY STATEMENT

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

**Pretreatment:**

The surfaces to be coated with TEROSON WT S3000 AQUA have to be clean, dry and free of rust, oil, grease, dust and other contamination. Areas not to be coated should be properly covered. Bare sheet steel must always be coated with wash primer prior to coating with TEROSON WT S3000 AQUA.

**Application:**

TEROSON WT S3000 AQUA is applied with the Henkel UBC-Gun from 1-l-cans. Recommended application pressure is 3 - 5 bar. Shake the can well before use. Fine surface structures can be obtained with the spray gun.

**Overpainting**

TEROSON WT S3000 AQUA can be painted over with water born or solvent-based paints. Due to the manifold paint systems existing in the market preliminary tests should always be carried out.

**Waterborne paints**

TEROSON WT S3000 AQUA is overpaintable with water borne paints at the earliest after 6 hours (mat surface) and up to 72 hours after application.

**Conventional (solvent-based) paints**



TEROSON WT S3000 AQUA is overpaintable with conventional (solvent based) paints after full drying and up to 72 hours after application.

TEROSON WT S3000 AQUA is a fast-drying thick layer system.

In the case of accelerated drying by using an airstream system or an air pistol, it has to be taken into account that the quickly formed skin on the surface is not ripped and blown off onto wet material because this could lead to crack formation and affect the surface.

#### **Cleaning:**

Equipment and contaminated parts should be cleaned with water immediately after use, if necessary also use an aqueous detergent. Pure solvent based cleaners can't be used for cleaning (coagulation).

Once TEROSON WT S3000 AQUA has dried it can only be removed mechanically.

#### **Classification:**

Please refer to the corresponding **Material Safety Data Sheets** for details on:

- Hazards identification**
- Transport information**
- Regulatory information**

#### **Storage:**

Frost sensitive	yes
Recommended storage temperature	10 to 25 °C
Shelf life	12 months

#### **Disclaimer**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS)

including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

#### **Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1



For the most direct access to local sales and technical support visit: [www.henkel.com/industrial](http://www.henkel.com/industrial)