

TEROSON® BOND ALL-IN-ONE PRIMER

Known as Teroson® PU 8519P
July 2020

PRODUCT DESCRIPTION

TEROSON® BOND ALL-IN-ONE PRIMER provides the following product characteristics:

Technology	Primer
Chemical Type	Polyurethane
Appearance (uncured)	Black liquid
Components	One component - requires no mixing
Viscosity:	Liquid
Cure	Humidity
Application	Surface pretreatment
Environmental temperature at application	-5 to 45°C (23 to 113°F)
Material application temperature	5 to 35°C (41 to 95°F)
In service temperature	-40 to 90°C (-40 to 194°F)
Short exposure (up to 1 hr)	120°C (248°F)
Specific Benefits	• Excellent adhesion on glass, ceramic, paint, plastics and remaining beads • Simple process • UV resistant • Fast evaporation

TEROSON® BOND ALL-IN-ONE PRIMER is a thin liquid, solvent-containing masking aid based on polyurethane. The product is notable for its excellent covering properties and its good UV-stability. The primer is suitable for promoting the adhesion of other PUR adhesives/sealants to glass, glass ceramic, various plastics, metals and can also be used for PUR-coated glasses and remaining beads. Teroson® BOND ALL-IN-ONE PRIMER is also suitable as corrosion protection for small flange damages. It is free from chlorinated hydrocarbons and aromatic solvents. Typical applications include the bonding of front, rear and side screens to the body of passenger, utility, special and rail vehicles.

TYPICAL PROPERTIES

Tested @ 23 °C/50 RH

Specific Gravity	0.98
Solids, %	35
Drying time, minutes (1C adhesive)	2
Drying time, minutes (2C adhesive)	15
Open time, hours	8

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions For Use

Surface Pretreatment

The surfaces to be coated must be dry, free of oil, dust, grease and other components or residues which would adversely affect adhesion. The surface must be cleaned and pretreated with Teroson® VR 10 or Teroson® BOND GLASS CLEANER. Technical Data Sheet of recommended cleaner has to be observed.

Preparation

Prior to use, shake the aluminum bottle vigorously by hand for at least 1 minute. A steel ball is provided in the bottle to assist mixing. This should move freely after three to four shakes.

Application

TEROSON® BOND ALL-IN-ONE PRIMER may be applied thinly and evenly with felt applicator or Teroson® BOND SPONGE. Let the primed surface evaporate as stated before the direct glazing adhesive is applied. A second application on the same point should be avoided, as partially dried primer will be softened again which can adversely affect adhesion properties. The optimal application temperature is between 5 to 30 °C. In exceptional cases the application can be done at higher temperatures. A higher reaction speed will be noticed.

Handling Precautions:

TEROSON® BOND ALL-IN-ONE PRIMER must be handled in a manner applicable to highly flammable materials and in compliance with relevant local regulations.

Special care must be taken to avoid contact of the product or its vapor with a flame or any electrical equipment that is not flame proofed.

The solvent can affect certain plastics or coatings. It is recommended to check all surfaces for compatibility before use.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal storage: 15°C to 25°C. Storage below 5°C or greater than 25°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Product Specification

The technical data contained herein are intended as reference only and are not considered specifications for the product.

Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

Approval and Certificate

Please contact Henkel representative for related approval or certificate of this product.

Data Ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23±2°C / 50±5% RH

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1