



MULTYFILLER EXPRESS

C19

VERSION: 240712
Page: 1/5

ACRYLIC 2K 4:1 PRIMER

DEFINITION

MULTYFILLER EXPRESS is a two-component acrylic primer filler for bodywork repair. In the development of the product, two characteristics have been carefully enhanced: its quality and ease of application in the workshop.

MULTYFILLER EXPRESS possesses a high isolating quality and an excellent adhesion to putties, fillers and properly sanded hardened paints.

PHYSICAL CHARACTERISTICS

Nature:	Acrylic 2K
Colour:	ME0 - white ME1 - light grey ME3 - medium grey ME6 - black
Specific weight:	1,60 kg/l at 20°C

	<i>High build filler</i>	<i>Primer Surfacer</i>	<i>Non sanding</i>	
Dry film thickness:	70-90 microns	50 microns	30 microns	Per coat
Solids content:	73%	64%	64%	Mixing application
VOC:	438 g/l Multyfiller Express 495 g/l	535 g/l	533 g/l	Mixing application 2004/42/EC - IIB(c1)(540)
Yield:	9 m ² /l	12 -18 m ² /l	16 - 18 m ² /l	Per coat

AUXILIARY PRODUCTS

P4000 Slow hardener
P5000 Standard hardener
P6000 Fast hardener
S322 Standard thinner
NS21 Non sanding convertor


SURFACE PREPARATION

SANDING PROCESS		Putty	Paints OEM	Cataphoresis	Plastic*
	P240	✓	✓	✓	✓
	DA93	✓	✓	✓	✓

NON SANDING PROCESS		Putty	Paints OEM	Cataphoresis	Plastic*
	P400	✓	✓	✓	✓
	DA93	✓	✓	✓	✓

(*) Additional information in the appendix.

MIXING RATIO

		High build filler		Primer Surfacer		Non sanding	
		Vol	Weight	Vol	Weight	Vol	Weight
	Multyfiller Express	4	100	4	100	3	100
	Hardener	1	15	1	15	1,5	30
	NS21	-	-	-	-	1	19
	S322	0 / 10%	0	1	14	-	-
	F/4 a 20°C	50"		19"		16"	
	P4000	20' - 40' (*)		20' - 40'		20'	
	P5000	20' - 40' (*)		20' - 40'		15'	
	P6000	15' - 35' (*)		15' - 35'		10'	

(*) Pot life data adding 5% of thinner.

APPLICATION METHOD

		<i>High build filler</i>	<i>Primer Surfacers</i>	<i>Non Sanding</i>
	HVLP	1,7 - 1,9 mm	1,5 - 1,7 mm	1,3 - 1,4 mm
		2 - 3 bar	2 - 2,5 bar	2 - 2,5 bar
	Coats	2	2	1 - 2
	20°C	5'	5'	3'

DRYING TIMES

		<i>High build filler</i>	<i>Primer Surfacers</i>	<i>Non sanding</i>
	P4000 - P5000	-	-	Min 15' Max 60'
	P4000	2 h	1,5 h	-
	P5000	2 h	1,5 h	> 1 h *
	P6000	1,5 h	1 h	-
	P4000 - P5000	30'	30'	-
	FLASH OFF	5'	5'	-
	FULL BAKE	7'	7'	-

(*) In case of superficial imperfections, it can be sanded after 15' at 20°C

SANDING

		<i>High build filler</i>	<i>Primer Surfacers</i>	<i>Non sanding</i>
 ORBIT 3 - 5	INITIAL	P360	P400	-
	FINAL	P600	P600	SANDING PAD MICROFINE
	INITIAL	P600	P600	-
	FINAL	P800	P800	P1000

COLOUR TABLE

<i>Grey Choice</i>	<i>Colours</i>	<i>Mixing ratio % peso</i>				<i>Recommended finishes</i>
R1		100:0 (ME0:ME6)	100:0:0 (ME0:ME3:ME6)	-	-	White Yellow Orange
R2		94:6 (ME0:ME6)	90:10:0 (ME0:ME3:ME6)	100:0 (ME1:ME6)	100:0:0 (ME1:ME3:ME6)	Red
R3		60:40 (ME0:ME6)	0:100:0 (ME0:ME3:ME6)	70:30 (ME1:ME6)	0:100:0 (ME1:ME3:ME6)	Light Green, light blue and light grey. Metallic light green, blue, red and grey. Metallic yellow, beige and orange
R4		35:65 (ME0:ME6)	0:60:40 (ME0:ME3:ME6)	40:60 (ME1:ME6)	0:60:40 (ME1:ME3:ME6)	Dark green, blue and grey. Metallic dark green, blue and grey
R5		0:100 (ME0:ME6)	0:0:100 (ME0:ME3:ME6)	0:100 (ME1:ME6)	0:0:100 (ME1:ME3:ME6)	Black Metallic black

EQUIPMENT CLEANING

Clean with a cleaning thinner before the product hardens.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheets. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

SHELF LIFE

One year in unopened original packaging.

APPENDIX: PLASTIC APPLICATION

Use Omniplast to improve adhesion to plastics:

- For an increase in productivity, add the additive together with the primer.
- For excellent adhesion results, apply before priming. In as little as 10-15 minutes, it will be time to apply Multifiller Express.

		<i>Surfacer</i>	<i>Non-sandable</i>
		<i>Weight</i>	<i>Weight</i>
WITHIN THE PRIMER	Multifiller Express	100	100
	Hardener	15	30
	NS21	-	19
	S322	2	-
	Omniplast	12	6
BEFORE PRIMING	Apply directly on a well prepared and degreased surface. It has excellent adhesion to PP, ABS, PC/PBT, etc.		

(*) For more information, please refer to the Omniplast TDS available on our official website.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO S.A.U reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

All clauses contained herein apply to any future changes or modifications.
For any additional technical information please consult with our Customer Service or our Technical Department.